

Technical Datasheet

DESCRIPTION

Terluran GP-22 is an easy-flow, general purpose injection molding grade with high resistance to impact and heat distortion; intended for a wide range of applications, particularly in the housings sector.

FEATURES

- Excellent colorability
- Medium flow
- Good impact resistance
- Good heat distortion resistance
- High quality surface finish and gloss

APPLICATIONS

- Injection molding
- Appliance housings
- Household and sanitary appliances
- Toys
- Automotive components

Property, Test Condition	Standard	Unit	Values
Rheological Properties			
Melt Volume Rate 220 °C/10 kg	ISO 1133	cm ³ /10 min	19
Mechanical Properties			
Izod Notched Impact Strength, 23 °C	ISO 180/A	kJ/m ²	26
Izod Notched Impact Strength, -30 °C	ISO 180/A	kJ/m ²	8
Charpy Notched Impact Strength, 23° C	ISO 179	kJ/m ²	22
Charpy Notched Impact Strength, -30° C	ISO 179	kJ/m ²	8
Charpy Unnotched, 23° C	ISO 179	kJ/m ²	180
Charpy Unnotched, -30° C	ISO 179	kJ/m ²	100
Tensile Stress at Yield, 23° C	ISO 527	MPa	45
Tensile Strain at Yield, 23° C	ISO 527	%	2.6
Tensile Modulus	ISO 527	MPa	2300
Nominal Strain at Break, 23 °C	ISO 527	%	10
Flexural Strength	ISO 178	MPa	65
Hardness, Ball Indentation	ISO 2039-1	MPa	97
Thermal Properties			
Vicat Softening Temperature VST/B/50 (50°C/h, 50N)	ISO 306	°C	96
Vicat Softening Temperature, VST/A/50 (50°C/h, 10N)	ISO 306	°C	105

Terluran GP-22

Acrylonitrile Butadiene Styrene (ABS)



Driving Success. Together.

Property, Test Condition	Standard	Unit	Values
Heat Deflection Temperature A; (annealed, 1.8 MPa)	ISO 75	°C	94
Heat Deflection Temperature B; (annealed, 0.45 MPa)	ISO 75	°C	99
Coefficient of Linear Thermal Expansion	ISO 11359	10 ⁻⁶ /°C	80 - 110
Thermal Conductivity	DIN 52612-1	W/(m K)	0.17
Electrical Properties			
Dissipation Factor (100 Hz)	IEC 60250	-	48E-4
Dissipation Factor (1 MHz)	IEC 60250	-	79E-4
Relative Permittivity (100 Hz)	IEC 60250	-	2.9
Relative Permittivity (1 MHz)	IEC 60250	-	2.8
Volume Resistivity	IEC 60093	Ohm*m	1E13
Surface Resistivity	IEC 60093	Ohm	1E13
Other Properties			
Density	ISO 1183	kg/m ³	1040
Water Absorption, Saturated at 23°C	ISO 62	%	1
Moisture Absorption, Equilibrium 23°C/50% RH	ISO 62	%	0.22
Yellowness Index	DIN 6167	-	13
Processing			
Linear Mold Shrinkage	ISO 294-4	%	0.4 - 0.7
Melt Temperature Range	ISO 294	°C	220 - 260
Mold Temperature Range	ISO 294	°C	30 - 60
Injection Velocity	ISO 294	mm/s	200
Drying Temperature		°C	80
Drying Time		h	2 - 4

Typical values for uncolored products

SUPPLY FORM

Terluran® is delivered as spherical pellets. The bulk density of the pellets is from 0.55 to 0.65 g/cm³. Standard Packaging unit: 25 kg PE-bag on palette, shrunk or wrapped with PE film or delivery in silo trucks. PE bags should not be stored outside. In dry areas with normal temperature control, Terluran pellets can be stored for relatively long periods of time without any change in mechanical properties. Under poor storage conditions, Terluran absorbs moisture, but this can be removed by drying.

PRODUCT SAFETY

No adverse effects on the health of processing personnel have been observed if the products are correctly processed and the production areas are suitably ventilated. For styrene, acrylonitrile and 1,3-butadiene the maximum allowable workplace concentrations must be observed according to the pertaining national regulations. In Germany, the following limit values are valid (Oct. 2002): styrene, MAK-value: $20 \text{ ml/m}^3 = 86 \text{ mg/m}^3$; acrylonitrile, TRK-value: $3 \text{ ml/m}^3 = 7 \text{ mg/m}^3$ and 1,3-butadiene, TRK-value: $5 \text{ ml/m}^3 = 11 \text{ mg/m}^3$. According to EU directive 67/548/EWG, Annex I and TRGS 905 (Oct. 2002), acrylonitrile and 1,3-butadiene are classified as carcinogenic, category 2 ('substances which should be regarded as if they are carcinogenic to man') and 1 (substances known to be carcinogenic to man), respectively. Experience has shown that during appropriate processing of Terluran with suitable ventilation the values obtained are well below the limits mentioned above. TRGS 402 (Germany) can be used for determining and assessing the concentrations of hazardous substances in the air within working areas. Inhalation of gaseous degradation products, such as those which may arise on severe overheating of the material or during pumped evacuation, must be avoided. Further information can be found in our Terluran safety data sheets.

DISCLAIMER

The above information is provided in good faith. Styrolution is not responsible for any processing or compounding which may occur to product finished articles, packaging materials or their components. Further, Styrolution MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN OR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Responsibility for use, storage, handling and disposal of the products described herein is that of the purchaser or end user.