

TYPICAL PROPERTIES OF TOYOLAC 920 555

Typical Properties	Test Method	Test Conditions	Unit	Typical Value
Melt Flow Rate	ISO 1133	220°C / 10kg	g/10min	25
Charpy Impact Strength, notched	ISO 179 / 1eA	23°C	kJ/m ²	9
Deflection Temperature Under Load	ISO 75	120°C/hr, 1.8MPa	°C	77
Tensile Yield Stress	ISO 527	50mm/min	MPa	54
Tensile Elongation	ISO 527	50mm/min	%	17
Tensile Modulus	ISO 527	1mm/min	MPa	2540
Flexural Stress	ISO 178	2mm/min	MPa	77
Flexural Modulus	ISO 178	2mm/min	MPa	2260
Density	ISO 1183	-	kg/m	1090

Toray Plastics Malaysia Sdn Bhd. (Head Office)
 2628, MK1 SPT, Lorong Perusahaan 4 FIZ, Prai, 13600, Penang, Malaysia
 Tel: 604-3988088 Fax: 604-3908975
 Email : sales.tpm@toray.com.my
www.torayplastics.com

