

Low Density Polyethylene IP2418

Description:

Good processability, high fluidity, flexibility and mechanical strength. It does not contain additives.

Application:

Injection molding and blends with EVA for foams.

Control Properties:

	ASTM Methods	Units	Values
Melt Flow Rate (190/2.16)	D 1238	g/10 min	24
Density	D 792	g/cm ³	0.919

Typical Properties:

 Plaque Properties^a

	ASTM Methods	Units	Values
Tensile Strength at Yield	D 638	MPa	9
Tensile Strength at Break	D 638	MPa	8
Tensile Elongation at Break	D 638	%	160
Flexural Modulus – 1% secant	D 790	MPa	300
Shore D Hardness	D 2240	-	49
Vicat Softening Temperature at 10 N	D 1525	°C	82
Environmental Stress Cracking Resistance ^b	D 1693	h/F50	1
Rigidity	D 747	MPa	320
Fragility Temperature	D 746	°C	< -70

(a) Test specimens prepared from compression molded sheet made according to ASTM D 4703.

(b) Compression molded 2 mm thickness, 0.3 mm notched-plaques. 10% Igepal. 50°C.

Recommended Processing Conditions:

Recommended processing conditions for:

1) Blends with EVA:

-Temperature profile: 100 to 150°C.

2) Injection molding:

-Temperature profile: 120 to 180°C.

The optimum processing conditions will vary according to the type of equipment used and cannot be considered as performance guarantee.

Final Remarks:

1. This resin meets the requirements for olefin polymers as defined in 21 CFR, section 177.1520 issued by FDA – Food and Drug Administration in force on the date of publication of this specification. The additives present are covered in appropriate regulation by FDA
2. The information presented in this Data Sheet reflects typical values obtained in our laboratories, but should not be considered as absolute or as warranted values. Only the properties and values mentioned on the Certificate of Quality are considered as guarantee of the product.
3. In some applications, Braskem has developed tailor-made resins to reach specific requirements.
4. In case of doubt regarding utilization, or for other applications, please contact our Technical Assistance.
5. For information about safety, handling, individual protection, first aids and waste disposal, please see MSDS. CAS Registry number: 009002-88-4.
6. The mentioned values in this report can be changed at any moment without Braskem previous communication.
7. Braskem does not recommend this grade for packages, parts or any kind of product manufacture that will be used for storage or contact with solution that will have internal contact with human body.
8. The content of this Data Sheet replaces previous revisions published for this product.
9. This resin does not contain the substance Bisphenol A (BPA, CAS # No. 80-05-7) in its composition.