



Technical Support:

Polymer Technology Services Centre
PO Box 72
Modderfontein 1645
South Africa

Sales office:

Sasol Polymers
PO Box 2525
Randburg 2125
South Africa

Tel: +27 (0)11 458 0700

Fax: +27 (0)11 458 0734

Tel: +27 (0)11 790 1413

Fax: +27 (0)11 344 0287

Date of Issue: August 2013

www.sasol.com/polymers

Sasol Polymers PP: ESV265

Features

- High flow
- Narrow molecular weight distribution
- Particularly suitable for injection moulding of articles where good transparency (high clarity) and excellent surface gloss are required
- Contains nucleating agent which ensures rapid crystallisation, resulting in improved cycle times due to shorter cooling times

Applications

Injection moulding

- Food containers
- Cosmetic containers
- Household and domestic articles
- Caps and closures
- Aerosol dust covers
- Stationery items

Additives

- General purpose
- Nucleation (high clarity)
- Mould release

MFR: 35 g/10min


Material properties (typical values not to be construed as specifications)

	Value	Unit	Test method
Rheological properties			
Melt mass-flow rate - MFR (230/2.16)	35	g/10min	ISO 1133
Moulding shrinkage - S_{Mp} / S_{Mn}	1.2/1.2	%	ISO 294-4
Mechanical properties			
Flexural modulus	1150	MPa	ISO 178
Tensile modulus of elasticity	1200	MPa	ISO 527-2/1A/1
Tensile stress at yield	29	MPa	ISO 527-2/1A/50
Tensile strain at yield	11	%	ISO 527-2/1A/50
Tensile strain at break	>50	%	ISO 527-2/1A/50
Charpy notched impact strength (23°C)	5.0	kJ/m ²	ISO 179-1/1eA
Charpy notched impact strength (0°C)	2.5	kJ/m ²	ISO 179-1/1eA
Ball indentation hardness - HB	50	N/mm ²	ISO 2039-1
Thermal properties			
Melting temperature - DSC	150	°C	ISO 11357-3
Heat deflection temperature - HDT/A (1.8 MPa)	46	°C	ISO 75-2
Heat deflection temperature - HDT/B (0.45 MPa)	70	°C	ISO 75-2
Vicat softening temperature - VST/A 120 (10N)	130	°C	ISO 306
Vicat softening temperature - VST/B 120 (50N)	70	°C	ISO 306
Other properties			
Density	0.905	g/cm ³	ISO 1183-1
Haze (1.0/2.0mm injection moulded plaques)	6.0/17	%	ISO 14782

Typical processing conditions

Injection moulding

Melt temperature 220 - 280°C



Packaging

Sasol Polymers polyolefin resins are supplied in pellet form packed in 25kg bags. Alternative packaging modes for polypropylene resins are available for selected grades.

Handling

Workers should be protected from the possibility of skin or eye contact with molten polymer. Safety glasses and heat resistant gloves are suggested as a minimal precaution to prevent possible mechanical or thermal injuries to the eyes and skin. Fabrication areas should be ventilated to carry away fumes or vapours.

Conveying equipment should be designed to prevent accumulation of fines or dust particles that are contained in all polyolefin resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. Sasol Polymers recommend the conveying system used:

- be equipped with adequate filters
- is operated and maintained in such a manner to ensure no leaks develop
- that adequate grounding exists at all times

Sasol Polymers further recommend that good housekeeping be practised throughout the manufacturing facility. Polymer pellets may pose a slippage hazard if spilled.

Storage

As ultraviolet light may cause a change in the material properties, all polyolefin resins should be protected from direct sunlight during storage. Under cool, dry, dark conditions Sasol Polymers polyolefin resins are expected to maintain their original material and processing properties for at least 18 months.